

Publication number: JP8196617
 Publication date: 1996-08-06
 Inventor: SHIKINAMI YASUO; IKADA
 YOSHITO; GEN JIYOUKOU;
 TSUTA KAORU; BOUYA
 HIDEKAZU
 Applicant: TAKIRON CO; BIOMATERIAL
 UNIVERSE KK
 Classification:
 - international: **A61L27/00; A61L27/00; (IPC1-7):
 A61L27/00**
 - European:
 Application number: JP19950268999 19950925
 Priority number(s): JP19950268999 19950925

[View INPADOC patent family](#)

[View list of citing documents](#)

[Report a data error here](#)

Abstract of JP8196617

PURPOSE: To provide a surgical material which has the same as bone or a little higher than that on compressive bending strength and compressive bending elastic modulus, by melt-molding a polylactic acid polymer having high molecular weight under a specified adjusted condition and drawing and cutting it. **CONSTITUTION:** This surgical material is an in vivo degradation absorbable material which is composed exclusively of a polylactic acid with viscosity average molecular weight of 300,000 to 600,000 or lactic acid-glycolic acid copolymer, thereby the surgical material having toughness and excellent hydrolysis-resistance is obtained by melt-molding these polymers and further cutting the drawn molding. On this occasion, the molding is cutting-worked into any shape of a plate, a pin, a machine screw, or a screw for bone conjugation. The compressive bending strength of the molding is $1.6 \times 10^{<3>}$ kg/cm $^{<2>}$ or more, the compressive bending elastic modulus is $5.0 \times 10^{<2>}$ kg/mm $^{<2>}$ or more, and the viscosity average molecular weight is 200,000 or more. Thereby, high compressive bending strength, the compressive bending elastic modulus and hydrolysis-resistance can be ensured.

Data supplied from the [esp@cenet](#) database - Worldwide